

Technical Datasheet

5652

Description

A 60 durometer, red, Natural Rubber material designed to optimal re-sealability when punctured with minimal bleed characteristics

Physical Properties	Actual Value	Spec. Value
---------------------	--------------	-------------

Original Properties – cured 30 minutes@310F (154C)

Specific Gravity	1.44
Hardness (Shore A)	65.0
Tensile Strength	2498 psi (17.22 Mpa)
Elongation (%)	440%
Tear Strength, Die C Method	208 ppi



All information supplied by or on behalf of Pawling Engineered Products, Inc. in relation to its products, whether in the nature of data, recommendations or otherwise, is believed reliable, but Pawling Engineered Products assumes no liability whatsoever in respect of application, processing or use made of the information, or any consequences thereof.